



VPUR5600
POLYURETHANE TOPCOAT 5600

Descriptive notes High quality clear polyurethane topcoat, general purpose.

Gloss Versions	5	10	20	30	40	50	60	80

USAGE

Suitable for	Cabinet doors	Panelling	Internal doors and shutters	Stylish furniture	Furniture	Chairs	Artisans
Method of application		Air mixing spray painting	Airless spray painting				

MAIN PROPERTIES

Filling	High	Easy Application	High
Transparency	High	Yellowing Resistance	Medium
Drying	Medium/ fast	Scratch Resistance	High

PREPARATION OF THE PRODUCT

	Code	%	Descriptive notes
Recommended thinner	DILL0202	20+30	
Other thinners			
Recommended hardener	INLL0101	50	
Other hardeners			
Accelerant.			

CHEMICAL-PHYSICAL CHARACTERISTICS		APPLICATION CHARACTERISTICS		DRYING	
Specific gravity (kg/l) ±0.03	0,99	N° of coats	1	Dust free (min)	18
Solids Content (%) ±1	48	Qty. per coat (g/m²)	100+120	Touch dry (min)	50
Viscosity DIN 4 (20°C) 4	65 ÷ 75				
Pot-Life at 20°C (h)	2			Stackable (h)	16

Additional information: Basecoat sanding, we recommend 320+400 abrasive paper. The surface should be clean, free from waxes, oils or dust.
 •Application Notes
 Conventional air gun: viscosity D4 15 sec. - nozzle 1.0+1.2 - air pressure 2 +3 bar.
 Airmix: viscosity D4 15 sec. - nozzle (kremlin) 0.9 - air pressure 0.5+1 bar.

WARNING Our data sheets are drawn up on the basis of average results of our trials. However our tech tips are given in good faith but without guarantee. In fact, several media, conditions of application, plant and dilutions are an integral part of the final result and often beyond our control. The user must try the products supplied to test whether suitable to your needs. For our part we guarantee the continuity of the chemical-physical characteristics.
 Warning: it is the user's responsibility to provide that the application is in properly ventilated environment hygienic and in accordance with standards and accident prevention regulations currently in force.

Revision n° 11	Revision 09/10/20
	Date 18

Printed:	09/10/2018
----------	------------