

AC

## WTFO0190

WATERBASED BASECOAT 190

Descriptive notes

CUAL

Clear thixotropic waterborne basecoat, 1-pack or 2-pack.

## USAGE

Suitable for	Cabinet doors	Internal doors and shutters	Panelling		
Method of application	Spray	Automatic spraying	Air mixing spray painting	Airless spray painting	

## MAIN PROPERTIES

Filling	High		Sanding	High	
Drying	Medium/ Slow		Resistance to overcoating	Medium	

## PREPARATION OF THE PRODUCT

	Code	%	Descriptive notes
Recommended thinner	Acqua	5÷10	
Other thinners			
Recommended hardener	INUR0350	0÷10	
Other hardeners			
Accelerant.			

CHEMICAL-PHYSICAL CHA	APPLICATION CHARACTERISTICS			DRYING					
Specific gravity (kg/l) ±0.03	1,02	N° of coats		1 - 2		Dust free (min)	60		
Solids Content (%) ±1 30		Qty. per coat (g/m²)		80 -	90 Touch dry (min)		120÷240		
Viscosity DIN 4 (20°C)	55"÷60" CF6								
Pot-Life at 20°C(h)	30'					Sanded (h)		24	
						Stackable (h)		24	
Additional information:	•Sanding the substrate using 150+180 sandpaper and clean the surface after sanding. During application, keep the product and the substrate at a temperature of at least 15°C. The use of coating devices not in perfect order may cause major defects in the coating film. •APPLICATION INSTRUCTIONS• Air gun: nozzle 1.9+2.5, air pressure 2+3 bar; Airmix: nozzle 9+11, air pressure 0.5+1 bar, Airless: nozzle 9+11. Wash immediately after use the tools with water and detergent. Store the product in room where the temperature does not fall below 5°C. If properly stored, the shelf-life is 12 months.								
Overcoatings with Topcoat type	Waterborne								
WARNING Our data sheets are drawn up on the basis of average results of our trials. However our tech tips are given in good faith but without guarantee.   In fact, several media, conditions of application, plant and dilutions are an integral part of the final result and often beyond our control. The user must try the products supplied to test whether suitable to your needs. For our part we guarantee the continuity of the chemical-physical characteristics.   Warning: it is the user's responsibility to provide that the application is in properly ventilated environment hygienic and in accordance with standards and accident prevention regulations currently in force.									
	Revision 27/11/2 Date 19	20	0		Print	ed: 27/11/2	019		
UCRO COATINICS S.D.A									

ICRO COATINGS S.P.A.

Via Bedeschi, 25 24040 Chignolo D'Isola (BG) Italia Tel +39 035 999 711 fax +39 035 999 712 Mail info@icro.it p.iva 02597000161