



WTVE6000--
CONVERTER ALL'ACQUA TRASP. 6000 OP.

Descriptive notes •High quality clear waterborne topcoat for all types of spray equipments. It can be used only in 2-Pack topcoat. The WTVE6000-- is studied for really high performances in terms of Chemical, stain and scratch resistant. For those reasons is ideal for kitchens. In combination with Basecoat WTFO0100 if you want the "Natural Look Effect"

Gloss Versions	05	10						
-----------------------	----	----	--	--	--	--	--	--

USAGE

Suitable for	Cabinet doors	Internal doors and shutters	Panelling	Furniture			
Method of application	Spray	Air mixing spray painting	Electrostatic spray				

MAIN PROPERTIES

Filling	High	Easy Application	High
Transparency	High	Yellowing Resistance	High
Drying	Medium	Scratch Resistance	High

PREPARATION OF THE PRODUCT

	Code	%	Descriptive notes
Recommended thinner	Water	6→15	
Other thinners			
Recommended hardener	INUR0601	20	
Other hardeners			
Accelerant.			

CHEMICAL-PHYSICAL CHARACTERISTICS		APPLICATION CHARACTERISTICS		DRYING	
Specific gravity (kg/l) ±0.03	1.02	N° of coats	1	Dust free (min)	20
Solids Content (%) ±1	35	Qty. per coat (g/m²)	120	Touch dry (min)	90→120
Viscosity DIN 6 (20°C) 6	45"-60"			Dry in oven for perfect resistant	3h @40-45°C
Pot-Life at 20°C (h)	45-60min.			Stackable (h)	24

Additional information:

- Sanding the substrate using 280+320 sandpaper and clean the surface after sanding.
- Store the product in room where the temperature does not fall below 5°C.
- If properly stored, the shelf-life is 12 months.
- During application, keep the product and the substrate at a temperature of at least 15°C.
- The use of coating devices not in perfect order may cause major defects in the coating film.
- Wash immediately after use the tools with water and detergent.

WARNING Our data sheets are drawn up on the basis of average results of our trials. However our tech tips are given in good faith but without guarantee. In fact, several media, conditions of application, plant and dilutions are an integral part of the final result and often beyond our control. The user must try the products supplied to test whether suitable to your needs. For our part we guarantee the continuity of the chemical-physical characteristics.
Warning: it is the user's responsibility to provide that the application is in properly ventilated environment hygienic and in accordance with standards and accident prevention regulations currently in force.

Revision n° 1	Revision 08/09/20
	Date 22

Printed:	29/11/2022
----------	------------